



IMPORTED TIMBER

31

Species: *Acer saccharum* Marsh.

Standard Trade Name: American rock maple

Common Names: Sugar maple, hard maple

1. Size of tree / type of forest: A tall to medium sized deciduous hardwood that is found in an area ranging from the Appalachian mountain range of North-east America to Canada.

2. Wood description: Heartwood is pale brown to pale red-brown. Sapwood creamy, but not always clearly differentiated from the heartwood, and up to 13 cm wide. Texture is fine and even. Grain usually straight but wavy grain is sometimes present. Fine brown lines of tissue marking the extremities of the growth rings give a distinctive figure to the tangential surface. Other grain patterns include curly, birdseye, quilted and fiddleback.

3. Wood density:

Green density (kg/m ³):	N/A
Air-dry density (kg/m ³):	About 730 kg/m ³
Basic density (kg/m ³):	N/A

4. Drying and shrinkage:

	<u>Tangential Shrinkage (%)</u>	<u>Radial Shrinkage (%)</u>
Before reconditioning:	6.0	3.0
After reconditioning:	N/A	N/A

5. Workability: Not easy to work, with tools requiring frequent sharpening, but finishes to a smooth surface. Glues satisfactorily. The timber has a good resistance to splitting though pre-drilling is advisable. Stains and polishes well, which complements its natural lustre. Good for turning and steam bending. Has outstanding resistance to abrasion.

6. Durability Class: 4. Sapwood is susceptible to *Lyctus* borer attack.

7. Strength Groups: S4 and SD4.

8. Strength Properties:

Property	Units	Green	Dry
Modulus of Rupture	MPa	69	109
Modulus of Elasticity	MPa	11000	13000
Max Crushing Strength	MPa	28	54
Hardness	kN	4.3	6.4

9. Uses: Flooring (especially for bowling alleys, squash courts and ballrooms), shoe lasts, textile bobbins, musical instruments (e.g. piano actions), handles, laminated golf club heads, decorative veneer, furniture kitchen utensils and butchers blocks.

10. Availability: Limited availability in Western Australia.

BACKGROUND INFORMATION

1. Size of tree and type of forest

Small trees have average heights up to 15 m, medium 15 to 30 m, and large over 30 m. Types of forest are sclerophyll (with closed canopy), woodland (with scattered trees), or rain forest. Diameter breast height is stem diameter at 1.3 m above ground.

2. Wood description

For example, sapwood and heartwood colour, grain, figure

3. Wood density (kg/m³)

Green density is the density of wood in the living tree, defined as green mass divided by green volume, and useful for estimating transport costs. It varies with season and growing conditions. Air-dry density is the average mass divided by volume at 12 per cent moisture content (this is the average environmental condition in the coastal capital cities around Australia).

Basic density is oven-dry mass divided by green volume. This measure has the advantage that moisture content variations are avoided.

4. Drying and shrinkage

As wood dries, it shrinks more in the tangential direction (i.e. parallel to the growth rings) than it does in the radial direction (i.e. at right angles to the growth rings). The figures given are shrinkage from green to 12 per cent moisture content, before and after steam reconditioning treatment. Reconditioning recovers any cells that may have collapsed during drying, and is essential for species such as the ash-type eucalypts.

5. Workability

Comments are made on the comparative ease or difficulty of turning, nailing and bending, on susceptibility to splitting and other working properties.

6. Durability

The CSIRO Durability Classes are based on the performance in ground of outer heartwood when exposed to fungal and termite attack. Class 1 gives more than 25 years life, Class 2 gives 15 to 25 years, Class 3 gives 8 to 15 years, and Class 4 less than eight years. The ratings are not relevant to above-ground use. In late 1996, CSIRO published revised ratings, which include termite susceptibility.

7. Strength grouping

In grading of structural timber, each species is allocated a ranking for green timber of S1 (strongest) to S7, and for seasoned timber SD1 (strongest) to SD8.

Minimum values for strength groups for green timber (units are MPa)

Strength property	S1	S2	S3	S4	S5	S6	S7
Modulus of rupture	103	86	73	62	52	43	36
Modulus of elasticity	16300	14200	12400	10700	9100	7900	6900
Maximum crushing strength	52	43	36	31	26	22	18

Minimum values for strength groups for seasoned timber (units are MPa)

Strength property	SD1	SD2	SD3	SD4	SD5	SD6	SD7	SD8
Modulus of rupture	150	130	110	94	78	65	55	45
Modulus of elasticity	21500	18500	16000	14000	12500	10500	9100	7900
Maximum crushing strength	80	70	61	54	47	41	36	30

8. Strength Properties

Values are from Bootle, K.R. (1983). 'Wood in Australia. Types, properties and uses'. (McGraw-Hill)

9. Uses

Various past and potential uses are given, but the list is obviously not conclusive.

10. Availability

Timber from many species is available only near the areas that the trees grow naturally or in plantations. Imported timbers and their current availability are identified.